

# DNP

## R300

### General Purpose Resin

### Technical Data Sheet



#### Product Description

R300's extensive label adaptability and high print speed capability make it the most diverse resin of its kind. It outperforms the competition in abrasion and solvent resistance, uses less print energy and is designed with DNP's standard anti-static and backcoat properties to protect and extend the life of printheads. And, like all DNP ribbons, R300 is an industry leader in edge definition producing dark, dense images for improved scan rates.

#### Applications



Automotive



Chemicals



Electronics



Food & Beverage



Health & Beauty



Inventory & Logistics



Outdoor



Pharmaceutical

#### Recommended Substrates

##### Synthetics

- ✓ Polyester
- ✓ Polypropylene
- ✓ Polyethylene
- ✓ Polyolefin
- ✓ Vinyl

#### Performance Characteristics

- ✓ Heat resistant up to 170°C
- ✓ Excellent print quality at high speeds using less print energy
- ✓ Extreme durability and solvent resistance
- ✓ Extensive label adaptability expanding application options
- ✓ Unbeatable edge definition for dark, dense images and improved scan rates
- ✓ DNP's specially formulated backcoating for printhead protection
- ✓ Most economical resin with DNP's unmatched abrasion resistance
- ✓ Anti-static for easy handling and extended printhead life

More Info



## RIBBON PROPERTIES

Description	Result	Test Method
Ink	Resin	
Color	Black	Visual
Total Thickness	5.8 ± 0.8μ	Weight
Base Film Thickness	4.5 ± 0.4μ	Weight

## DURABILITY OF PRINTED IMAGE

Description	Result	Test Method
Print Density	> 1.80	Densitometer
Smudge Resistance	A*	Colorfastness Tester - 100 Cycles @ 500 Grams with Cotton Cloth
Scratch Resistance	A*	Colorfastness Tester - 50 Cycles @ 200 Grams with Stainless Steel Pointed Tip

Label Stock: Top-coated Polyester      Print Speed: 6 IPS

\*American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.



The information on this data sheet was obtained in DNP laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.

## DNP IMAGINGCOMM ASIA SDN. BHD.

PL0 676, Jalan Nikel 4, Kawasan Perindustrian Pasir Gudang, 81700 Pasir Gudang, Johor, Malaysia



+607-257 8440



ttrsales@dnp-g.com



www.asia-dnpribbons.com



DNP Imagingcomm Asia TTR