



# TR6070Plus

## Chemical Resistant Resin

### Technical Data Sheet



### Product Description

TR6070P is unique in the industry — the best resin ribbon for printing on coated and synthetic paper substrates. It is also able to withstand environmental temperatures of up to 220° C (428° F) making it perfect for applications like heat tunnel passage. TR6070P uses remarkably low print energy settings while producing high quality heat resistant bar codes. This ribbon’s design incorporates DNP’s standard anti-static and backcoat properties that protect the printhead, and also prints with DNP’s unmatched edge definition producing clean, extremely durable, dense bar codes every time.

### Applications



Automotive



Chemicals



Electronics



Health & Beauty



Inventory & Logistics



Outdoor



Pharmaceutical

### Recommended Substrates

#### Synthetics

- ✓ Polyester

#### Specialty Materials

- ✓ Polyimide
- ✓ Top-coated vinyl
- ✓ PVC cards
- ✓ PET cards

### Performance Characteristics

- ✓ Heat resistant up to 220°C
- ✓ Halogen-free
- ✓ Unmatched in abrasion and solvent resistance
- ✓ High density printing ensuring edge definition
- ✓ Anti-static for easy handling and extended printhead life
- ✓ DNP’s specially formulated backcoating for printhead protection

More Info



## RIBBON PROPERTIES

Description	Result	Test Method
Ink	Resin	
Color	Black	Visual
Total Thickness	6.9 ± 0.9μ	Weight
Base Film Thickness	4.5 ± 0.4μ	Weight

## DURABILITY OF PRINTED IMAGE

Description	Result	Test Method
Print Density	> 2.07	Densitometer
Smudge Resistance	A*	Colorfastness Tester - 400 Cycles @ 500 Grams with Cotton Cloth
Scratch Resistance	A*	Colorfastness Tester - 50 Cycles @ 200 Grams with Stainless Steel Pointed Tip

Label Stock: Top-coated Polyester

Print Speed: 4 IPS

\*American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.



The information on this data sheet was obtained in DNP laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.

## DNP IMAGINGCOMM ASIA SDN. BHD.

PLO 676, Jalan Nikel 4, Kawasan Perindustrian Pasir Gudang, 81700 Pasir Gudang, Johor, Malaysia



+607-257 8440



ttrsales@dnp-g.com



www.asia-dnpribbons.com



DNP Imagingcomm Asia TTR